

ロット番号	樹種名	材幅	材厚	スパン	日付				
09101600	スギ	105	105	2700	2009/10/16				
NO	水AV	重量	水判定	強度(Tonf/cm <sup>2</sup> )	たわみ1	たわみ2	荷重1,	荷重2	区分
001	17.2	1425	2	78.1	2.38	10.81	50.2	241.2	2
002	16.6	987	2	88.5	2.11	9.53	50.4	241	3
003	15.8	1315	2	120.8	1.66	7.11	50.1	241.1	5
004	16.6	1267	2	96.5	1.86	8.68	50.2	241.2	3
005	18.8	1559	2	133.9	1.59	6.51	50.1	241.2	5
006	14.7	1378	1	110	1.93	7.91	50.3	241.2	4
007	15.8	1133	2	94.8	2.04	8.98	50.2	241	3
008	17.2	1373	2	97	1.95	8.74	50.1	241.1	3
009	17.7	1376	2	122.3	1.69	7.07	50.1	241	5
010	15.4	1351	2	111.5	1.33	7.23	50.5	241.3	4
011	18.2	1410	2	105.2	1.42	7.67	50.3	241.1	4
012	16.4	1425	2	116.2	1.45	7.1	50.8	241.3	4
013	17.5	1329	2	127.5	1.48	6.64	50.4	241.2	5
014	17.7	1397	2	126.3	1.62	6.83	50.4	241.3	5
015	16	1410	2	114.6	1.4	7.14	50.5	241.4	4
016	15.6	1425	2	113.1	1.7	7.52	50.5	241.4	4
017	17.4	1505	2	131.7	1.41	6.41	50.1	241.1	5
018	18.6	1468	2	119.1	1.73	7.25	50.5	241.2	4
019	17	1321	2	102.3	1.88	8.31	50.3	241.2	4
020	16.7	1315	2	111.1	1.4	7.31	50.6	241	4
021	15.3	1311	2	104.8	1.76	8.04	50.3	241.2	4
022	18.5	1632	2	99.2	1.63	8.27	50.2	241.3	3
023	16.5	1379	2	106.4	1.79	7.98	50.2	241.3	4
024	17	1467	2	128.9	1.24	6.34	50.6	241.3	5
025	17.9	1498	2	134.6	1.34	6.23	50.3	241.2	5
026	14.3	1214	1	87.3	2.23	9.76	50.4	241.1	3
027	15.3	1232	2	95.8	1.96	8.82	50.4	241	3
028	12.5	1160	1	96.7	2	8.81	50.1	241.2	3
029	15.8	1242	2	90.5	2.23	9.5	50.2	241	3
030	12.7	1263	1	95.5	1.98	8.87	50.2	241.2	3
031	17.9	1099	2	85.5	2.22	9.93	50	241.2	3
032	15.6	1303	2	98.1	1.78	8.47	50.6	241.1	3
033	12.1	1261	1	98.1	1.84	8.55	50.4	241.3	3
034	13.9	1575	1	72.9	2.31	11.32	50.4	241	2
035	14.7	1155	1	93.8	1.86	8.86	50.7	241.1	3
036	13.4	1525	1	130.6	1.33	6.37	50.1	241.1	5
037	14.1	1422	1	133.5	1.43	6.35	50.4	241	5
038	14	1254	1	98.3	1.88	8.57	50.3	241.1	3
039	14	1434	1	134.1	1.5	6.4	50.7	241.3	5
040	13.2	1531	1	142.5	1.25	5.87	50.2	241.2	6
041	16	1287	2	120.3	1.57	7.03	50.6	241.2	5
042	14.9	1238	1	104.4	1.71	8.02	50.1	241.2	4
043	15.3	1266	2	100.9	1.68	8.2	50.2	241	4
044	14.6	1290	1	112.4	1.59	7.44	50.5	241.2	4
045	13	1510	1	137.5	1.25	6.03	50.5	241.1	5
046	16.5	1494	2	73.1	2.37	11.37	50.3	241.3	2
047	17.9	1403	2	116.3	1.61	7.26	50.5	241.2	4
048	14.5	1217	1	100.2	1.87	8.43	50.4	241.1	4
049	14.1	1447	1	99.4	1.94	8.56	50.3	241.2	3
050	17.2	1247	2	124.1	1.64	6.94	50.4	241.2	5
051	15.3	1177	2	63.9	2.59	12.9	50.1	241.2	2
052	13.4	1410	1	104.9	1.82	8.1	50.2	241.3	4
053	18.4	1431	2	92.1	2.03	9.18	50.1	241.1	3
054	16.1	1553	2	119.6	1.32	6.82	50.4	241.2	4
055	12.8	1093	1	101.7	1.79	8.25	50.4	241	4
056	15	1320	2	120	1.49	6.97	50.5	241.3	5

057	16.6	1108	2	97.2	1.78	8.55	50.5	241.5	3
058	12	1525	1	126.1	1.57	6.79	50.4	241.3	5
059	15.8	1151	2	82.6	2.45	10.42	50.3	241.2	3
060	14.9	1169	1	105.2	1.9	8.15	50.3	241	4
061	17.5	1123	2	83.3	2.32	10.22	50.1	241.1	3
062	15.3	1641	2	106.3	2.02	8.21	50.3	241.2	4
063	18.8	1430	2	103.5	1.87	8.22	50.5	241.1	4
064	17.8	1268	2	117.6	1.69	7.28	50.5	241.2	4
065	15.9	1530	2	100.2	2.03	8.59	50.5	241.2	4
066	16.6	1546	2	101.6	1.77	8.23	50.7	241.1	4
067	17.7	1274	2	83	2.3	10.23	50.3	241.2	3
068	18.3	1367	2	120	1.52	7	50.4	241.2	5
069	16.8	1260	2	53.6	3.46	15.73	50.2	241.2	1
070	14	1247	1	63.7	2.7	13.02	50.3	241.2	2
071	18.2	1424	2	77.4	2.4	10.9	50.2	241.2	2
072	15.4	983	2	59.8	3.05	14.04	50.2	241	1
073	16.7	1258	2	83	1.72	9.64	50.3	241.1	3
074	16.7	1658	2	79.8	2.23	10.47	50.4	241.2	2
075	16.7	1342	2	107.2	1.75	7.88	50.3	241	4
076	17.1	1200	2	105.3	1.67	7.92	50.5	241.4	4
077	17	1348	2	102.9	1.77	8.16	50.5	241.3	4
078	15.1	984	2	105.1	2.47	8.73	50.3	241.2	4
079	14.7	1018	1	64.2	2.86	13.11	50	241.1	2
080	17.3	1190	2	83.2	2.46	10.36	50.4	241	3
081	14.6	1168	1	94.4	2.56	9.54	50.1	241.2	3
082	18.1	1735	2	93.2	2.09	9.15	50.3	241.3	3
083	16.8	1366	2	92	1.86	9	50.4	241	3
084	16.6	1666	2	89.5	1.94	9.29	50.2	241.1	3
085	18	1427	2	69.8	2.2	11.63	50.1	241.1	2
086	17.6	1223	2	100.9	1.9	8.42	50.3	241.1	4

ロット番号	樹種名	材幅	材厚	スパン	日付				
09101601	スギ	105	105	3600	2009/10/16				
NO	水AV	重量	水判定	強度(Tonf/cm <sup>2</sup> )	たわみ1	たわみ2	荷重1,	荷重2	区分
001	17.4	1873	2	95.4	4.59	15.8	50.2	181.1	3

ロット番号	樹種名	材幅	材厚	スパン	日付				
9101602	ヒノキ	120	120	5400	2009/10/16				
NO	水AV	重量	水判定	強度(Tonf/cm <sup>2</sup> )	たわみ1	たわみ2	荷重1,	荷重2	区分
001	21.7	4426	3	115.3	7.29	25.5	50.1	180	4
002	22.8	4438	3	110.2	6.4	25.47	50.2	180.2	4
003	18.1	4901	2	104.2	5.29	25.46	50.2	180.2	4
004	18.1	4441	2	109.8	6.3	25.42	50.1	180	4
005	14.4	4010	1	115.3	6.39	24.62	50	180	4
006	17.8	4430	2	111.7	5.95	24.77	50.2	180.2	4

ロット番号	樹種名	材幅	材厚	スパン	日付				
09101700	スギ	105	150	3600	2009/10/17				
NO	水AV	重量	水判定	強度(Tonf/cm <sup>2</sup> )	たわみ1	たわみ2	荷重1,	荷重2	区分
001	8.2	1596	1	71	0.99	8.35	50.4	492.2	2
002	12.3	1682	1	77.4	0.87	7.6	51.2	492.1	2
003	16.7	2200	2	83.9	3.37	14.07	50.1	370.3	3
004	12.3	2491	1	68.8	2.58	15.62	50.2	370.2	2
005	17.7	2729	2	79.1	1.93	13.27	50.2	370.2	2
006	17.7	3192	2	82.6	2.06	12.92	50.2	370.2	3
007	19.3	2714	2	74.4	1.94	13.98	50.4	370.3	2
008	18.1	2368	2	67.4	2.09	15.38	50.2	370.1	2
009	19.3	2870	2	64.6	3.52	17.4	50.3	370.2	2
010	16.6	2279	2	85.2	1.87	12.39	50.3	370	3

011	17.4	2278	2	70.3	2.39	15.14	50.3	370.1	2
012	17.3	3441	2	73.7	2.26	14.43	50.2	370.2	2
013	15.6	2632	2	89.6	1.52	11.52	50.4	370.1	3

ロット番号	樹種名	材幅	材厚	スパン	日付				
09101701	スギ	105	180	2700	2009/10/17				
NO	水AV	重量	水判定	強度(Tonf/cm <sup>2</sup> )	たわみ1	たわみ2	荷重1,	荷重2	区分
001	13.9	2954	1	89	1.1	7.74	50.6	415.1	3
002	17.9	3132	2	68.8	1.25	9.84	50.8	415.3	2
003	16.6	4060	2	66.2	1.37	10.3	50.3	415.1	2
004	15.4	3030	2	65.9	1.34	10.32	50.2	415	2
005	11.2	2705	1	64.9	1.54	10.65	50.4	415.1	2
006	18.7	2554	2	51.5	1.98	13.47	50.3	415.1	1
007	17.3	2730	2	78.3	1.24	8.8	50.3	415.3	2
008	18.9	2556	2	69.3	1.17	9.7	50.3	415.1	2
009	17.2	2573	2	61.9	1.53	11.09	50.2	415.2	2
010	17.8	3500	2	76	1.43	9.21	50.3	415	2
011	16.8	2808	2	76.3	1.21	8.97	50.1	415.2	2
012	17.3	2981	2	61.3	1.5	11.15	50.5	415.1	2
013	12.6	2720	1	68.9	1.53	10.12	50.2	415.3	2
014	18.1	2656	2	80.9	0.43	6	50.4	709.3	3
015	18.5	2240	2	60.9	0.69	8.09	50.6	709.3	2
016	11.6	2557	1	79.1	0.64	6.34	50.1	709.3	2

ロット番号	樹種名	材幅	材厚	スパン	日付				
09101702	スギ	105	210	2700	2009/10/17				
NO	水AV	重量	水判定	強度(Tonf/cm <sup>2</sup> )	たわみ1	たわみ2	荷重1,	荷重2	区分
001	15	2335	2	55.7	0.58	7.65	50.9	965.3	1
002	22.9	2251	3	64.3	0.46	6.59	50.6	965.3	2
003	22.3	3264	3	65.1	0.49	6.54	50.6	965.6	2
004	23.7	3109	3	77.4	0.3	5.39	50.8	965.5	2
005	20.7	3614	3	66.5	0.42	6.34	50.6	965.1	2
006	14.5	2478	1	89.4	0.3	4.71	50.8	965.7	3
007	21.5	2577	3	48.9	0.58	8.64	50.7	965.2	1
007	—	—	—	55.1	0.49	7.64	50.5	965.2	1

ロット番号	樹種名	材幅	材厚	スパン	日付				
09101703	スギ	105	210	3600	2009/10/17				
NO	水AV	重量	水判定	強度(Tonf/cm <sup>2</sup> )	たわみ1	たわみ2	荷重1,	荷重2	区分
001	18.7	4002	2	61.5	0.98	10.19	50.4	605.2	2
002	20.5	3389	3	71.7	0.85	8.75	50.4	605.4	2
003	21.4	3617	3	62	0.94	10.08	50.3	605.4	2
004	14.8	4207	1	84.6	0.63	7.33	50.4	605.2	3
005	15.9	3034	2	61.9	0.98	10.14	50.1	605.3	2
006	16.8	3122	2	57.2	1.09	10.99	50.1	605.1	1
007	17.2	3689	2	72.1	0.95	8.81	50.5	605.3	2

ロット番号	樹種名	材幅	材厚	スパン	日付				
09101704	スギ	105	240	3600	2009/10/17				
NO	水AV	重量	水判定	強度(Tonf/cm <sup>2</sup> )	たわみ1	たわみ2	荷重1,	荷重2	区分
001	18.6	4850	2	60.1	0.72	9.56	50.3	827.2	2
002	22.6	4675	3	57.5	0.83	10.07	50.6	827.1	1
003	23	4301	3	57.6	0.78	10	50.7	827.3	1

ロット番号	樹種名	材幅	材厚	スパン	日付				
09101705	スギ	105	270	2700	2009/12/15				
NO	水AV	重量	水判定	強度(Tonf/cm <sup>2</sup> )	たわみ1	たわみ2	荷重1,	荷重2	区分
001	24.4	5126	3	75.2	0.37	6.69	50.6	1040.4	2

002	20.5	4194	3	74.4	0.31	4.52	50.7	1596	2
003	22.3	4313	3	63.6	0.33	5.25	51.7	1595.6	2
004	13.2	3220	1	49	0.25	6.64	50.6	1595.7	1

ロット番号	樹種名	材幅	材厚	スパン	日付				
09101706	スギ	105	300	3600	2009/12/15				
NO	水AV	重量	水判定	強度(Tonf/cm <sup>2</sup> )	たわみ1	たわみ2	荷重1,	荷重2	区分
001	24.3	6631	3	65.3	0.38	10.67	50.9	1969.5	2
002	21.1	5360	3	58.3	0.48	12.01	51.3	1969.6	1
003	24.7	5253	3	63.1	0.45	11.1	51.1	1969.4	2

ロット番号	樹種名	材幅	材厚	スパン	日付				
09101707	スギ	105	360	2700	2009/12/15				
NO	水AV	重量	水判定	強度(Tonf/cm <sup>2</sup> )	たわみ1	たわみ2	荷重1,	荷重2	区分
001	17.6	5444	2	45.3	0.38	9.67	50.9	2126.2	1
002	22.4	4718	3	39.8	0.22	6.2	50.5	2835.9	1
003	22.9	4652	3	45.9	0.13	5.32	51.4	2836	1
004	23	5181	3	48.5	0.19	5.1	51.1	2836	1
005	20.5	6635	3	43.3	0.11	5.39	51.1	2835.7	1