

ロット番号	樹種名	材幅	材厚	スパン	日付				
10092201	スギ	105	105	2700	2010/10/12				
NO	水AV	重量	水判定	強度(Tonf/cm ²)	たわみ1	たわみ2	荷重1	荷重2	区分
1	12.4	1299	1	95.4	1.07	7.96	50.4	241.1	4
2	16.3	1124	2	76.8	1.98	10.56	50	241.3	3
3	12.8	1053	1	62.9	2.81	13.27	50.2	241.2	3
4	8.5	1151	1	59.6	3.04	14.08	50.1	241.1	3
5	7.7	1105	1	64.1	2.92	13.19	50	241.1	3
6	10.8	1051	1	62.4	2.74	13.28	50.2	241.1	3
7	6.4	1218	1	72.1	2.04	11.16	50.4	241.1	3
8	13.4	1339	1	107.6	1.84	7.95	50.2	241	5
9	12.8	1376	1	91.8	1.89	9.07	50.1	241.4	4
10	8.2	1154	1	72.5	2.65	11.74	50.1	241.3	3
11	13.9	993	1	86.7	2.11	9.69	50.3	241	4
12	6.6	1199	1	69.8	2.28	11.7	50.2	241	3
13	14	1254	1	88	1.63	9.11	50.3	241.2	4
14	16.5	1057	2	81.5	2.2	10.28	50	241.1	4
15	10.1	1023	1	90.7	2.07	9.33	50.1	241.1	4
16	7.9	1324	1	88.7	1.86	9.27	50.4	241.1	4
17	19.8	1226	2	79.9	2.48	10.72	50.1	241.1	4
18	8.8	1235	1	103.8	1.63	7.96	50.3	241	5
19	8.9	1189	1	78.4	2.22	10.61	50.1	241	3
20	7.7	1299	1	121.8	1.34	6.75	50	241.2	6
21	7.9	1256	1	97.1	1.88	8.66	50.1	241.1	4
22	18.9	1240	2	92.6	2.1	9.2	50.4	241.1	4
23	8.6	1238	1	73.8	2.04	10.96	50	241.1	3
24	21.6	1123	3	96.5	1.95	8.77	50.1	241	4
25	7.4	1189	1	65.2	2.85	12.94	50.2	241.2	3
26	8.7	1193	1	78.1	2.16	10.59	50.3	241.3	3
27	12.9	1125	1	95.6	1.83	8.71	50.2	241	4
28	13.2	1352	1	104.4	1.73	8.03	50.1	241	5
29	12.4	1029	1	98.5	1.81	8.5	50	241.1	4
30	27.3	923	4	82.4	2.04	10.02	50.2	241.1	4
31	7.7	1266	1	76.7	2.04	10.62	50.2	241.1	3
32	10.7	1066	1	92.5	2.05	9.17	50	241.1	4
33	10	1220	1	101.1	1.81	8.32	50.1	241.1	5
34	10.4	1032	1	68	2.64	12.32	50.2	241.1	3
35	10.9	1059	1	69	2.49	12.02	50.3	241.1	3
36	9	1117	1	75.4	2.44	11.17	50.1	241	3
37	6.9	1293	1	102.6	1.67	8.08	50.3	241.1	5
38	10.6	1041	1	94.8	1.92	8.85	50.3	241	4
39	20.2	913	3	74.4	2.4	11.25	50.2	241.2	3
40	11	1102	1	68.3	2.45	12.09	50.1	241.1	3
41	17.5	1126	2	95.9	1.75	8.61	50.2	241.1	4
42	9.1	1114	1	86.5	1.97	9.59	50	241.2	4
43	8.7	1123	1	69.9	2.45	11.87	50	241	3
44	9.7	1069	1	92.5	2.1	9.22	50.1	241.1	4
45	21	1157	3	84.2	1.74	9.56	50	241.1	4
46	8.6	1145	1	78.7	2.17	10.53	50.1	241.1	3
47	8.3	1135	1	75.4	2.26	11	50	241.1	3
48	8	1160	1	72.7	2.74	11.8	50.4	241.4	3
49	10.3	1205	1	72.8	2.42	11.47	50.1	241.3	3
50	8.3	1123	1	78.1	2.45	10.88	50.2	241.2	3
51	17.4	1053	2	72.1	2.42	11.55	50.3	241.2	3
52	9.7	1090	1	74.6	2.38	11.21	50.2	241.4	3
53	19.6	1236	2	72.1	2.28	11.41	50.1	241.1	3
54	10	1154	1	71.6	2.46	11.66	50	241.1	3
55	13.3	1142	1	87.3	2.2	9.74	50.1	241.1	4
56	10.7	1257	1	117.2	1.43	7.05	50.3	241.3	5
57	7.6	1211	1	83.6	2.1	9.97	50.1	241.1	4
58	10.6	1080	1	68.1	2.27	11.93	50.2	241.1	3
59	10.8	974	1	61	2.9	13.69	50.1	241	3
60	8.6	1147	1	66.3	2.64	12.56	50.1	241	3
61	16.1	1129	2	66.6	2.56	12.44	50.1	241.1	3
62	18.3	1020	2	72.2	2.5	11.61	50.2	241	3
63	11.1	1268	1	91.1	1.95	9.18	50.1	241.2	4
64	10.5	1078	1	69.3	2.58	12.07	50.1	241	3
65	13.8	1171	1	73.3	2.49	11.47	50.1	241.1	3
66	8.8	1248	1	120	1.43	6.91	50.2	241	6
67	11.6	1257	1	74.2	2.43	11.29	50.3	241	3
68	24.3	1002	3	79	2.18	10.52	50	241.1	4
69	10.5	1120	1	78.2	2.21	10.64	50.1	241.3	3

70	15.3	1155	2	102	1.85	8.31	50	241.1	5
71	9.4	1162	1	69.8	2.5	11.93	50.1	241.1	3
72	7.5	1159	1	81.5	2.03	10.1	50.1	241	4
73	9.2	1159	1	97.7	1.6	8.34	50.2	241.2	4
74	26.1	1016	4	60.2	2.68	13.61	50.1	241	3
75	7.9	1138	1	63.6	2.77	13.12	50.1	241.1	3
76	11.1	1154	1	96.8	1.89	8.7	50.2	241.4	4
77	18.6	1299	2	90.5	1.95	9.22	50.2	241	4
78	8	1233	1	84.4	2.13	9.92	50.2	241	4
79	9.4	1287	1	115.2	1.68	7.39	50.3	241.1	5
80	22.5	1038	3	67.4	2.59	12.36	50.2	241.2	3
81	10.7	1072	1	80	2.34	10.57	50	241	4

ロット番号	樹種名	材幅	材厚	スパン	日付				
10092301	スギ	105	240	3600	2010/10/12				
NO	水AV	重量	水判定	強度(Tonf/cm ²)	たわみ1	たわみ2	荷重1,	荷重2	区分
1	17.8	4214	2	85.6	0.49	6.7	50.6	827.4	4
2	18	4247	2	59.3	0.66	9.62	50.4	827.2	3
3	18.8	3661	2	73.7	0.27	7.48	50.2	827.3	3
4	19.4	3817	2	72.8	0.53	7.83	50.3	827.2	3
5	17.1	3708	2	98.1	0.38	5.8	50.5	827.4	4
6	21	3985	3	87.9	0.47	6.52	50.1	827.2	4

ロット番号	樹種名	材幅	材厚	スパン	日付				
10092302	スギ	105	240	2700	2010/10/12				
NO	水AV	重量	水判定	強度(Tonf/cm ²)	たわみ1	たわみ2	荷重1,	荷重2	区分
1	21.6	3189	3	67.9	0.34	5.48	50.6	1260.5	3
2	19.6	2826	2	85	0.28	4.39	50.5	1260.8	4
3	19.8	2715	2	53.3	0.32	6.87	50.3	1260.4	2
4	17.5	3351	2	78.9	0.21	4.64	50.5	1260.9	4
5	17.7	3424	2	95.7	0.26	3.91	50.8	1260.7	4
6	16.5	3625	2	65.1	0.2	5.56	50.7	1260.8	3
7	12.2	2705	1	74	0.24	4.96	50.7	1260.7	3
8	18	2752	2	78.1	0.22	4.69	50.5	1260.7	3
9	19.9	2678	2	64.8	0.21	5.6	50.9	1260.6	3
10	20.4	2892	3	69	0.24	5.3	50.3	1260.4	3
11	-	-	-	67.5	0.28	5.45	50.6	1260.6	3

ロット番号	樹種名	材幅	材厚	スパン	日付				
10092303	スギ	105	300	3600	2010/10/12				
NO	水AV	重量	水判定	強度(Tonf/cm ²)	たわみ1	たわみ2	荷重1,	荷重2	区分
1	22.2	5152	3	76.8	0.33	6.84	50.3	1477.5	3

ロット番号	樹種名	材幅	材厚	スパン	日付				
10092304	スギ	105	210	3600	2010/10/12				
NO	水AV	重量	水判定	強度(Tonf/cm ²)	たわみ1	たわみ2	荷重1,	荷重2	区分
1	21.3	3924	3	54	0.92	11.41	50.1	605	2
2	21	3493	3	68.7	0.92	9.17	50.2	605.4	3

ロット番号	樹種名	材幅	材厚	スパン	日付				
10092305	スギ	105	180	3600	2010/10/12				
NO	水AV	重量	水判定	強度(Tonf/cm ²)	たわみ1	たわみ2	荷重1,	荷重2	区分
1	17.2	3342	2	75.4	1.09	8.93	50.3	415.1	3
2	17.3	3251	2	78.6	1.06	8.59	50.3	415.3	3
3	16.5	2757	2	71	1.37	9.71	50.2	415.2	3
4	18.2	3126	2	63.9	1.37	10.63	50.1	415.3	3
5	17.8	3016	2	70.9	1.25	9.6	50.2	415.3	3
6	17.7	2942	2	82.6	1.12	8.29	50.1	415.5	4

ロット番号	樹種名	材幅	材厚	スパン	日付				
10092306	スギ	105	180	2700	2010/10/12				
NO	水AV	重量	水判定	強度(Tonf/cm ²)	たわみ1	たわみ2	荷重1,	荷重2	区分
1	16.4	2055	2	72	0.54	6.8	50.5	709.4	3
2	17.6	2413	2	75.1	0.49	6.49	50.7	709.4	3
3	18.2	2181	2	63.3	0.61	7.73	50.4	709.2	3
4	17.2	2616	2	94.1	0.3	5.09	50.6	709.3	4
5	17.2	1941	2	82.4	0.51	5.98	50.2	709.3	4
6	18.1	2334	2	73.3	0.4	6.55	50.5	709.7	3
7	17.8	1887	2	72.8	0.53	6.72	50.5	709.1	3

8	15.4	1987	2	62.5	0.62	7.83	50.3	709.2	3
9	15.5	1974	2	61.9	0.43	7.71	50.5	709.3	3

ロット番号	樹種名	材幅	材厚	スパン	日付				
10092307	スギ	105	150	3600	2010/10/12				
NO	水AV	重量	水判定	強度(Tonf/cm ²)	たわみ1	たわみ2	荷重1	荷重2	区分
1	16.9	2821	2	78.4	1.94	13.38	50	370.2	3
2	18	2612	2	70.3	2.08	14.83	50	370.1	3
3	18.3	2579	2	71.4	2.09	14.66	50.1	370.2	3
4	17.3	2306	2	64.9	2.24	16.04	50.2	370.1	3
5	16.2	2464	2	93.8	1.41	10.97	50.2	370.1	4
6	17.2	2298	2	84.2	1.63	12.29	50.2	370.4	4
7	17.4	2694	2	120.1	1.33	8.8	50.1	370.1	6
8	16	2179	2	85.8	1.76	12.21	50.2	370.1	4
9	17.3	2721	2	91.4	1.44	11.24	50.2	370	4
10	16.1	2329	2	91.4	1.68	11.49	50.1	370.1	4

ロット番号	樹種名	材幅	材厚	スパン	日付				
10092308	スギ	105	150	2700	2010/10/12				
NO	水AV	重量	水判定	強度(Tonf/cm ²)	たわみ1	たわみ2	荷重1	荷重2	区分
1	18	1781	2	74.3	1.05	8.08	50.4	492.4	3
2	18	1614	2	80.2	0.94	7.45	50.4	492.3	4
3	15.8	1499	2	74.9	0.94	7.91	50.5	492.1	3
4	13.5	1927	1	90.7	0.75	6.51	50.2	492.3	4
5	16.9	1994	2	78	0.94	7.64	50.2	492.2	3
6	16.5	1872	2	77	0.85	7.63	50.4	492.2	3
7	18.2	2041	2	91.1	0.74	6.48	50.1	492.2	4
8	17.6	1702	2	72.7	1.09	8.27	50.7	492.3	3

ロット番号	樹種名	材幅	材厚	スパン	日付				
10092309	スギ	105	105	2700	2010/10/12				
NO	水AV	重量	水判定	強度(Tonf/cm ²)	たわみ1	たわみ2	荷重1	荷重2	区分
1	16.5	1351	2	96.2	1.75	8.6	50.2	241.3	4
2	17.5	1357	2	111.5	1.57	7.6	50.3	241.1	5
3	18.2	1323	2	70.1	2.72	12.12	50	241.1	3
4	16.8	1357	2	99.3	1.97	8.59	50.3	241	5
5	17.5	1373	2	96.2	2.05	8.9	50.1	241.3	4
6	16.6	1519	2	117.3	1.8	7.41	50.3	241.2	5
7	18.1	1286	2	97.2	1.55	8.33	50.2	241.3	4
8	18.2	1235	2	104.4	1.31	7.6	50.4	241	5
9	16.5	1391	2	97.8	1.87	8.6	50.2	241.1	4
10	17.9	1199	2	94.3	2.07	9.06	50.1	241.3	4
11	16.5	1281	2	99.7	1.65	8.25	50.1	241	5
12	17.4	1281	2	96.7	1.62	8.43	50.2	241.2	4
13	18.1	1126	2	84.7	1.82	9.59	50.1	241.1	4
14	16.7	1293	2	102.5	1.87	8.29	50.2	241.1	5
15	17.1	1318	2	115.5	1.51	7.21	50.2	241.2	5
16	17.9	1268	2	112.5	1.49	7.33	50.4	241	5
17	17.3	1284	2	71.3	2.38	11.61	50.1	241.1	3
18	17.6	1611	2	115.4	1.51	7.21	50.3	241.1	5
19	16.5	1502	2	110.4	1.73	7.69	50.3	241.2	5
20	17.9	1374	2	106.5	1.6	7.78	50.3	241.2	5
21	17.5	1407	2	100.5	1.83	8.38	50.2	241.2	5
22	17.8	1397	2	111.6	1.62	7.52	50.1	241.1	5
23	18.4	1339	2	101.8	1.67	8.14	50.2	241.2	5
24	17.5	1141	2	81.3	2.07	10.16	50.3	241.2	4
25	17.3	1372	2	100.2	1.73	8.29	50.3	241	5
26	18.1	1399	2	119.6	1.37	6.88	50.1	241.3	6
27	18.5	1262	2	108.1	1.32	7.41	50.2	241.1	5
28	17.8	1256	2	110.8	1.58	7.52	50	241	5
29	16.8	1251	2	101.7	1.59	8.07	50.1	241.2	5
30	16.5	1425	2	77.3	2.19	10.7	50.3	241.1	3
31	19	1321	2	84.8	2.21	9.97	50.2	241.1	4
32	17.9	1297	2	103.8	1.81	8.16	50	241.2	5
33	18.6	1205	2	103.6	1.77	8.12	50.5	241.3	5
34	16.6	1379	2	99.3	1.62	8.24	50.4	241.2	5
35	18.5	1323	2	104.2	1.68	7.98	50.6	241.1	5
36	16.2	1500	2	81.6	2.22	10.29	50.1	241.1	4
37	18.1	1354	2	96.4	1.78	8.61	50.1	241.1	4
38	16.1	1554	2	98.2	1.78	8.48	50.2	241	4
39	17.9	1329	2	104.2	1.65	7.97	50.1	241.2	5

40	16.4	1355	2	96.1	1.67	8.52	50.3	241.2	4
41	17.3	1395	2	98.4	1.73	8.42	50.3	241.2	4
42	16.9	1250	2	80.6	2.1	10.26	50.2	241	4
43	16.1	1385	2	115	1.55	7.28	50.2	241.3	5
44	18.7	1181	2	86.3	2.17	9.79	50.3	241	4
45	17.8	1277	2	112.2	1.62	7.49	50.2	241.2	5
46	17.5	1317	2	114	1.55	7.32	50.2	241.1	5
47	18.5	1162	2	94.9	1.62	8.55	50.1	241	4
48	14.9	1357	1	112.1	1.34	7.21	50.3	241.2	5
49	16	1376	2	98.5	1.74	8.41	50.3	241	4
50	17.9	1433	2	116.6	1.22	6.87	50.1	241.2	5
51	18	1399	2	112.9	1.59	7.41	50.3	241	5
52	17.8	1312	2	102.6	1.87	8.28	50.3	241.1	5
53	17.9	1289	2	104.1	1.61	7.94	50.2	241.3	5
54	17	1101	2	83.8	2.24	10.1	50.1	241.2	4
55	15.6	1278	2	107.5	1.68	7.81	50.1	241.2	5
56	16.6	1338	2	102.9	1.81	8.2	50.3	241	5
57	16.1	1391	2	116.3	1.31	6.96	50.4	241	5
58	17	1257	2	98	1.86	8.58	50.1	241.2	4
59	16.6	1269	2	102.9	1.8	8.2	50.2	241.2	5
60	15.4	1355	2	114.9	1.61	7.33	50.5	241.2	5
61	16.3	1287	2	99.2	1.84	8.48	50.3	241.4	5
62	16.6	1451	2	102.9	1.92	8.32	50.1	241.2	5
63	16.4	1330	2	104.9	1.73	8	50.3	241.2	5
64	16.6	1312	2	68.7	2.53	12.12	50.2	241.3	3
65	17.4	1308	2	110.3	1.67	7.64	50.1	241.1	5
66	17.2	1373	2	96.7	1.82	8.62	50.3	241.1	4
67	18.2	1293	2	110.4	1.45	7.42	50	241.2	5
68	15.1	1663	2	119	1.63	7.17	50.1	241.4	6
69	18.3	1228	2	92.9	2.05	9.13	50.2	241.1	4
70	16.5	1436	2	118.3	1.54	7.1	50.3	241.1	5
71	18.1	1317	2	107.5	1.55	7.67	50.2	241.1	5
72	17.9	1281	2	110.3	1.61	7.57	50.4	241.1	5
73	16	1311	2	107.2	1.66	7.81	50	241.3	5
74	17.9	1213	2	88.5	2	9.44	50.1	241.1	4
75	17.6	1359	2	105.4	1.6	7.85	50.1	241.2	5
76	19	1323	2	99.6	1.6	8.22	50.2	241.4	5
77	18.6	1253	2	106.8	1.55	7.72	50.3	241.4	5
78	17.9	1329	2	99.8	1.62	8.21	50.1	241	5
79	17.3	1302	2	98.7	1.71	8.38	50.2	241.2	4
80	17.3	1317	2	105.5	1.63	7.86	50.4	241.1	5
81	17.2	1315	2	104.9	1.51	7.78	50.2	241.1	5
82	18.9	1196	2	76.2	2.33	10.96	50.3	241.2	3
83	17.1	1312	2	101.4	1.85	8.35	50	241.2	5
84	17.1	1315	2	102.4	1.62	8.05	50.2	241.3	5
85	16.3	1391	2	122.2	1.44	6.84	50	241.4	6
86	15.9	1408	2	115.6	1.59	7.29	50	241.1	5
87	17.4	1302	2	102.3	1.82	8.25	50.2	241	5
88	17.5	1281	2	99.3	1.78	8.41	50.2	241.2	5
89	17.2	1431	2	110	1.61	7.6	50	241.1	5
90	17.8	1392	2	102.9	1.68	8.08	50.3	241.3	5
91	17.9	1293	2	105.2	1.74	8	50.3	241.4	5
92	16.8	1373	2	98.4	1.78	8.47	50.2	241.1	4
93	18.3	1223	2	86	1.97	9.61	50.4	241.1	4
94	16.4	1347	2	96.1	1.94	8.8	50	241.3	4
95	17.6	1271	2	113.8	1.61	7.4	50.1	241.2	5
96	17.7	1290	2	109.7	1.43	7.42	50.4	241.1	5
97	17.1	1278	2	97.6	1.81	8.56	50.3	241.4	4
98	16.9	1320	2	107.2	1.74	7.88	50.2	241.1	5
99	17.9	1272	2	113.3	1.61	7.41	50.4	241.1	5
100	15.4	1426	2	114.6	1.54	7.28	50.3	241.1	5
101	16.5	1483	2	108.8	1.53	7.57	50.3	241	5
102	18.7	1290	2	76.5	2.48	11.08	50.2	241.1	3
103	17.3	1209	2	86.9	3.17	10.75	50.2	241.3	4
104	16.4	1105	2	77.1	3.22	11.75	50.3	241.1	3
105	17.8	1250	2	97.9	2.72	9.45	50	241.2	4
106	15.9	1389	2	58	2.81	14.15	50.2	241.1	2
107	16.6	1385	2	93	2.56	9.64	50.1	241.1	4
108	18.1	1188	2	94.7	3.38	10.33	50.1	241.1	4
109	16.8	1173	2	68.2	4.03	13.67	50.1	241	3

ロット番号	樹種名	材幅	材厚	スパン	日付
-------	-----	----	----	-----	----

10092310	スギ	105	105	3600	2010/10/12				
NO	水AV	重量	水判定	強度(Tonf/cm ²)	たわみ1	たわみ2	荷重1,	荷重2	区分
1	16.5	2062	2	87.3	5.13	17.38	50.2	181.1	4

ロット番号	樹種名	材幅	材厚	スパン	日付				
10092311	ヒノキ	120	120	5400	2010/10/12				
NO	水AV	重量	水判定	強度(Tonf/cm ²)	たわみ1	たわみ2	荷重1,	荷重2	区分
1	18.3	4764	2	94.6	7.69	29.9	50.1	180.1	4
2	18.6	4267	2	111.3	6.52	25.4	50	180	5
3	18.7	4103	2	100.2	7.57	28.55	50	180.1	5
4	19.4	4048	2	101.3	6.99	27.7	50.2	180	5

ロット番号	樹種名	材幅	材厚	スパン	日付				
10092500	スギ	120	120	2700	2010/10/12				
NO	水AV	重量	水判定	強度(Tonf/cm ²)	たわみ1	たわみ2	荷重1,	荷重2	区分
1	23.9	1604	3	53.7	1.96	13.6	50.4	360	2
2	21	1774	3	58.9	1.71	12.34	50	360.1	3
3	16.2	1442	2	88.8	1.19	8.24	50.5	360.3	4
4	19.4	1830	2	60.1	1.57	11.99	50.3	360.1	3

ロット番号	樹種名	材幅	材厚	スパン	日付				
10092501	スギ	120	120	2700	2010/10/12				
NO	水AV	重量	水判定	強度(Tonf/cm ²)	たわみ1	たわみ2	荷重1,	荷重2	区分
1	13.6	4226	1	92.8	7.8	30.43	50.1	180	4
2	15.5	4803	2	111.8	6.65	25.44	50.2	180.1	5
3	14.1	4299	1	118.5	7.12	24.86	50.1	180.2	5
4	17.5	4268	2	94.8	8.09	30.26	50.1	180.1	4
5	17.2	4276	2	103.8	7.37	27.59	50.2	180	5
1	16.6	1764	2	68.3	1.38	10.55	50.3	360.2	3
2	21.6	1787	3	54.3	2.1	13.64	50.1	360.1	2
3	25.9	1505	4	51.5	1.95	14.11	50.2	360.2	2
4	20.3	1847	3	71.5	1.51	10.27	50.2	360.2	3
5	28	1409	4	56.4	1.99	13.1	50.1	360.2	2
6	20.2	1888	3	67.8	1.71	10.95	50.1	360.2	3

ロット番号	樹種名	材幅	材厚	スパン	日付				
10092600	スギ	105	360	3600	2010/10/12				
NO	水AV	重量	水判定	強度(Tonf/cm ²)	たわみ1	たわみ2	荷重1,	荷重2	区分
1	22.8	6829	3	42.9	0.45	10.26	50.5	2126.5	2

ロット番号	樹種名	材幅	材厚	スパン	日付				
10092601	スギ	105	300	3600	2010/10/12				
NO	水AV	重量	水判定	強度(Tonf/cm ²)	たわみ1	たわみ2	荷重1,	荷重2	区分
1	24.1	6001	3	57	0.34	9.11	50.4	1477.4	2
2	20.5	6167	3	54.8	0.53	9.64	50.7	1477.5	2
3	20.2	5780	3	59.4	0.26	8.68	50.3	1477.4	3
4	20.4	5240	3	51.1	0.42	10.19	50.2	1477.4	2

ロット番号	樹種名	材幅	材厚	スパン	日付				
10092602	スギ	105	270	2700	2010/10/12				
NO	水AV	重量	水判定	強度(Tonf/cm ²)	たわみ1	たわみ2	荷重1,	荷重2	区分
1	21.9	3864	3	60.6	0.21	5.38	50.4	1595.8	3

ロット番号	樹種名	材幅	材厚	スパン	日付				
10092603	スギ	105	240	3600	2010/10/12				
NO	水AV	重量	水判定	強度(Tonf/cm ²)	たわみ1	たわみ2	荷重1,	荷重2	区分
1	23.1	4578	3	61	0.54	9.25	50.5	827.3	3

ロット番号	樹種名	材幅	材厚	スパン	日付				
10092604	スギ	105	210	2700	2010/10/12				
NO	水AV	重量	水判定	強度(Tonf/cm ²)	たわみ1	たわみ2	荷重1,	荷重2	区分
1	21.8	3236	3	90.8	0.3	4.64	51.3	965.5	4
2	22	3255	3	97.5	0.2	4.24	50.9	965.5	4
3	21.1	3081	3	76.6	0.3	5.44	51.2	965.6	3
4	22.5	3122	3	100	0.26	4.2	51.1	965.6	5
5	23.1	3639	3	73.8	0.29	5.63	50.8	965.5	3
6	23.4	2638	3	76.7	0.37	5.51	50.5	965.3	3
7	22.2	2686	3	64.1	0.46	6.61	50.7	965.4	3

8	22.1	2435	3	65.5	0.56	6.58	50	965.3	3
9	21.5	2319	3	69.2	0.18	5.87	51	965.5	3

ロット番号	樹種名	材幅	材厚	スパン	日付				
10092605	スギ	105	180	3600	2010/10/12				
NO	水AV	重量	水判定	強度(Tonf/cm ²)	たわみ1	たわみ2	荷重1,	荷重2	区分
1	11.7	3021	1	79.3	0.99	8.45	50.3	415.1	4
2	17.5	3049	2	83.3	0.81	7.91	50.4	415.1	4

ロット番号	樹種名	材幅	材厚	スパン	日付				
10092606	スギ	105	150	3600	2010/10/12				
NO	水AV	重量	水判定	強度(Tonf/cm ²)	たわみ1	たわみ2	荷重1,	荷重2	区分
3	18.7	3023	2	105.1	1.32	9.86	50.1	370.3	5
4	18	2756	2	79.3	2.19	13.51	50.1	370.3	4
5	18	2603	2	105.4	1.12	9.62	50.5	370.2	5
6	-	-	-	75	2.23	14.18	50	370	3
7	-	-	-	77.8	1.85	13.38	50.1	370.1	3

ロット番号	樹種名	材幅	材厚	スパン	日付				
10092607	スギ	105	150	2700	2010/10/12				
NO	水AV	重量	水判定	強度(Tonf/cm ²)	たわみ1	たわみ2	荷重1,	荷重2	区分
1	16.3	1791	2	96.1	1.19	4.24	50.8	492.4	4